



Florida  
Test



Total duration:  
12 months



EXPOSURE PERIOD:

FROM: **07/08/2012**

TO: **06/08/2013**

LAB. ID NUMBER: 27399  
POWDER COATING: DS 402  
HEAT TRANSFER FILM: 1404/02  
colour variation ( $\Delta E$ ): **3,34**  
residual gloss: **74%**

#### Technical Remarks

Residual gloss is sufficient but colour variation is very high so not acceptable for outdoor use.

### Technical opinion:

**Not for outdoor use**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### QUALIDECO REQUIREMENTS

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

