



Laboratory  
Test

No. 722



Device:  
QSun 3000



Total duration:  
1199



LAB. ID NUMBER: 59046  
POWDER COATING: DS 450  
HEAT TRANSFER FILM: 1409/02  
colour variation ( $\Delta E$ ): **1,58**  
residual gloss: **75%**

#### Technical Remarks

Good residual gloss and low colour variation ( $\Delta E$ ), after 1199 hours.

Technical Opinion:

**Suitable for  
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.