



Laboratory
Test


No. 682



Device:
Sol 3000RH



Total duration:
1060 h



LAB. ID NUMBER: 55659
POWDER COATING: 8G-096-A009
HEAT TRANSFER FILM: 1832/02
colour variation (ΔE): **0,39**
residual gloss: **76%**

Technical Remarks

Good residual gloss and normal colour variation (ΔE), after 1060 hours.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.