



Laboratory
Test


No. 450



Device:
QSun 3000



Total duration:
1045h



LAB. ID NUMBER: 38139
POWDER COATING: Colibri-018
HEAT TRANSFER FILM: 6058/01
Grey Scale: **5/4**
residual gloss: **81%**

Technical Remarks

Excellent residual gloss and low colour variation,
after 1045 hours.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.