



Laboratory
Test


No. 260



Device:
Solar 3000e



Total duration:
871h



LAB. ID NUMBER: 23869
POWDER COATING: DS 403
HEAT TRANSFER FILM: 1802/21L
colour variation (ΔE): **1,69**
residual gloss: **70%**

Technical Remarks

Excellent residual gloss and very low colour variation (ΔE), after 871 hours on decorated sample.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.