



Laboratory
Test

No. 592



Device:
Sol 3000RH



Total duration:
1251 h



LAB. ID NUMBER: 49472
POWDER COATING: DS 442
HEAT TRANSFER FILM: 2305/17
colour variation (ΔE): **0,74**
residual gloss: **80%**

Technical Remarks

Excellent residual gloss and normal variation (ΔE), after 1251 hours.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.