



Laboratory  
Test


No. 689



Device:  
QSun 3000N



Total duration:  
1243h



LAB. ID NUMBER: 57166  
POWDER COATING: 8G-055-A005  
HEAT TRANSFER FILM: 2803/02  
colour variation ( $\Delta E$ ): **1,03**  
residual gloss: **63%**

#### Technical Remarks

Good residual gloss and low variation ( $\Delta E$ ), after 1243 hours.

Technical Opinion:

**Suitable for  
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.