



Laboratory  
Test


No. 229



Device:  
Solar. 3000e



Total duration:  
1072h



LAB. ID NUMBER: 22707  
POWDER COATING: PE 411 + DS-0810S  
HEAT TRANSFER FILM: 5018/05L  
colour variation ( $\Delta E$ ): **3,85**  
residual gloss: **83%**

#### Technical Remarks

Excellent residual gloss but not acceptable colour variation ( $\Delta E$ ),  
after 1072 hours, for coating samples

Technical Opinion:

**NOT for  
outdoor use**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.