



Laboratory
Test


No. 738



Device:
QSun 3000



Total duration:
1163h



LAB. ID NUMBER: 59371
POWDER COATING: DS 742
HEAT TRANSFER FILM: 2523/03
colour variation (ΔE): 1,23
residual gloss: 53%

Technical Remarks

Sufficient residual gloss and low colour variation (ΔE), after 1163 hours.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.