



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 01/06/2021

TO: 01/06/2022

LAB. ID NUMBER: 50423
POWDER COATING: 8G-042-A005
HEAT TRANSFER FILM: 1823/22
Colour variation (ΔE): 2,58
residual gloss: 83%

Technical Remarks

Excellent residual gloss and normal colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

**Unexposed area
(reference)**

**Exposed
area**

