



Florida
Test



Total duration:
12 months



EXPOSURE PERIOD:

FROM: **27/11/2015**

TO: **19/12/2016**

LAB. ID NUMBER: 38363
POWDER COATING: DS 402
HEAT TRANSFER FILM: 2118/01
Colour variation (ΔE): **1,11**
residual gloss: **100%**

Technical Remarks

Excellent residual gloss and low colour variation (ΔE)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALICOAT REQUIREMENTS

The residual gloss shall be at least 50% of the original gloss.

The ΔE values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).

