



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 01/07/2022

TO: 01/07/2023

LAB. ID NUMBER: 52795
POWDER COATING: 9G-165-A005
HEAT TRANSFER FILM: 2504/10
Colour variation (ΔE): 1,78
residual gloss: 77%

Technical Remarks

Good residual gloss and normal colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

**Unexposed area
(reference)**

**Exposed
area**

