



Florida
Test



Total duration:
12 months



EXPOSURE PERIOD:

FROM: **23/05/2014**

TO: **27/05/2015**

LAB. ID NUMBER: 33978
POWDER COATING: DS 450
HEAT TRANSFER FILM: 1806/02
Colour variation (ΔE): **2,60**
residual gloss: **94%**

Technical Remarks

Excellent residual gloss and low colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALICOAT REQUIREMENTS

The residual gloss shall be at least 50% of the original gloss.

The ΔE values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).

