



Florida  
Test



Total duration:  
12 months



EXPOSURE PERIOD:

FROM: **20/08/2013**

TO: **21/08/2014**

LAB. ID NUMBER: 31936  
POWDER COATING: DS 403  
HEAT TRANSFER FILM: 2601/05  
Colour variation ( $\Delta E$ ): **1,99**  
residual gloss: **61%**

#### Technical Remarks

Sufficient residual gloss and low colour variation ( $\Delta E$ ).

### Technical Opinion:

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### QUALICOAT REQUIREMENTS

The residual gloss shall be at least 50% of the original gloss.

The  $\Delta E$  values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).

Unexposed area  
(reference)

Exposed  
area

