



Florida
Test



Total duration:
12 months



EXPOSURE PERIOD:

FROM: **25/07/2024**

TO: **25/07/2025**

LAB. ID NUMBER: 56481
POWDER COATING: DS-1739S
HEAT TRANSFER FILM: 1448/21
Colour variation (ΔE): **1,64**
residual gloss: **92%**

Technical Remarks

Excellent residual gloss and normal colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye

