



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 25/07/2024**

**TO: 25/07/2025**

LAB. ID NUMBER: 56677  
POWDER COATING: DS 753  
HEAT TRANSFER FILM: 2103/01  
Colour variation ( $\Delta E$ ): **0,66**  
residual gloss: **68%**

**Technical Remarks**

Good residual gloss and low colour variation ( $\Delta E$ ).

**Technical Opinion:**

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

**REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with the naked eye

**Unexposed area  
(reference)**

**Exposed  
area**

