



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 01/07/2023

TO: 01/07/2024

LAB. ID NUMBER: 56450
POWDER COATING: 9C-101-A032
HEAT TRANSFER FILM: 1448/21
Colour variation (ΔE): **1,45**
residual gloss: **96%**

Technical Remarks

Excellent residual gloss and normal colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

**Unexposed area
(reference)**

**Exposed
area**

