



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 25/07/2024**

**TO: 25/07/2025**

LAB. ID NUMBER: 56763  
POWDER COATING: DS 739  
HEAT TRANSFER FILM: 2504/04  
Colour variation ( $\Delta E$ ): 2,29  
residual gloss: 70%

#### **Technical Remarks**

Good residual gloss and normal colour variation ( $\Delta E$ ).

#### **Technical Opinion:**

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### **REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with the naked eye

**Unexposed area  
(reference)**

**Exposed  
area**

