



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 14/10/2022

TO: 16/10/2023

LAB. ID NUMBER: 55586
POWDER COATING: DS 1401
HEAT TRANSFER FILM: 2503/04
colour variation (ΔE): 1,73
residual gloss: 70%

Technical Remarks

Good residual gloss and low colour variation (ΔE)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

**Unexposed area
(reference)**

**Exposed
area**

