



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 25/07/2024**

**TO: 25/07/2025**

LAB. ID NUMBER: 56787  
POWDER COATING: 8G-042-A005  
HEAT TRANSFER FILM: 2507/07  
Colour variation ( $\Delta E$ ): **1,56**  
residual gloss: **62%**

#### **Technical Remarks**

Good residual gloss and low colour variation ( $\Delta E$ ).

#### **Technical Opinion:**

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### **REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with the naked eye

**Unexposed area  
(reference)**

**Exposed  
area**

