



Florida  
Test



Total duration:  
12 months



EXPOSURE PERIOD:

FROM: **27/11/2015**

TO: **19/12/2016**

LAB. ID NUMBER: 38374  
POWDER COATING: DS 439L  
HEAT TRANSFER FILM: 2101/02  
Colour variation ( $\Delta E$ ): **0,69**  
residual gloss: **100%**

#### Technical Remarks

Excellent residual gloss and low colour variation ( $\Delta E$ )

### Technical Opinion:

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### QUALICOAT REQUIREMENTS

The residual gloss shall be at least 50% of the original gloss.

The  $\Delta E$  values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).

Unexposed area  
(reference)

Exposed  
area

