



Florida
Test



Total duration:
12 months



EXPOSURE PERIOD:

FROM: **25/07/2024**

TO: **25/07/2025**

LAB. ID NUMBER: 56521
POWDER COATING: 8G-148-A009
HEAT TRANSFER FILM: 2516/10
Colour variation (ΔE): **0,47**
residual gloss: **96%**

Technical Remarks

Excellent residual gloss and low colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with
the naked eye

**Unexposed area
(reference)**

**Exposed
area**

