



Florida  
Test



Total duration:  
12 months



### EXPOSURE PERIOD:

FROM: **25/07/2024**

TO: **25/07/2025**

LAB. ID NUMBER: 56523  
POWDER COATING: DS 768  
HEAT TRANSFER FILM: 2516/10  
Colour variation ( $\Delta E$ ): **1,38**  
residual gloss: **66%**

### Technical Remarks

Good residual gloss and low colour variation ( $\Delta E$ ).

### Technical Opinion:

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with  
the naked eye

**Unexposed area  
(reference)**

**Exposed  
area**

