



Florida
Test



Total duration:
12 months



EXPOSURE PERIOD:

FROM: 25/07/2024

TO: 25/07/2025

LAB. ID NUMBER: 56536
POWDER COATING: DS 725
HEAT TRANSFER FILM: 2901/06
Colour variation (ΔE): 2,97
residual gloss: 62%

Technical Remarks

Good residual gloss and normal colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with
the naked eye

**Unexposed area
(reference)**

**Exposed
area**

