



Florida  
Test



Total duration:  
12 months



**EXPOSURE PERIOD:**

**FROM: 25/07/2024**

**TO: 25/07/2025**

LAB. ID NUMBER: 56944  
POWDER COATING: DS 425  
HEAT TRANSFER FILM: 2103/05  
Colour variation ( $\Delta E$ ): 2,63  
residual gloss: 51%

#### **Technical Remarks**

Sufficient residual gloss and normal colour variation ( $\Delta E$ ).

#### **Technical Opinion:**

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### **REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye

**Unexposed area  
(reference)**

**Exposed  
area**

