Florida Test

Total duration: 12 months

EXPOSURE PERIOD:

FROM: **05/08/2025**

TO: **13/08/2026**

LAB. ID NUMBER: 58157
POWDER COATING: 9C-101-A001
HEAT TRANSFER FILM: 1901/01
Colour variation (ΔE): **1,60**
residual gloss: **100%**

Technical Remarks

Excellent residual gloss and low colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS
The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye

