



TESTED FOR OUTDOOR USE



DS 739 + 2301/02



DS 797 + 2305/17



DS 753 + 1829/02



DS 742 + 1825/02



DS 742 + 1704/02



DS 0706S + 1001/09



DS 0706S + 1815/02




DS 0706S + 1414/05




DS 0718S + 2105/09



DS 0716S + 2106/02



DS 730 + 2105/01



DS 730 + 1407/01



DS 726 + 2507/07



DS 772 + 2507/18



DS 775 + 2510/06



DS 704M + 2501/15

Test Report: Accelerated Weat. Test, Florida Natural Exposure



Accelerated Weathering Test	Accelerated Weathering Test	Accelerated Weathering Test	Accelerated Weathering Test	Accelerated Weathering Test	Accelerated Weathering Test	Accelerated Weathering Test	Accelerated Weathering Test
LAB. ID NUMBER: 24264 POWDER COATING: DS 726 HEAT TRANSFER FILM: 2507/07L colour variation (ΔE): 2,3 residual gloss: 81%	LAB. ID NUMBER: 29120 POWDER COATING: DS 753 HEAT TRANSFER FILM: 1629/02 colour variation (ΔE): 1,16 residual gloss: 76%	LAB. ID NUMBER: 29116 POWDER COATING: DS 730 HEAT TRANSFER FILM: 2105/01 colour variation (ΔE): 0,36 residual gloss: 90%	LAB. ID NUMBER: 29117 POWDER COATING: DS 730 HEAT TRANSFER FILM: 1407/01 colour variation (ΔE): 1,2 residual gloss: 87%	LAB. ID NUMBER: 24325 POWDER COATING: DS 742 HEAT TRANSFER FILM: 1325/02L colour variation (ΔE): 0,99 residual gloss: 95%	LAB. ID NUMBER: 24193 POWDER COATING: DS 772 HEAT TRANSFER FILM: 2507/18 colour variation (ΔE): 1,06 residual gloss: 89%	LAB. ID NUMBER: 22766 POWDER COATING: DS-0706S HEAT TRANSFER FILM: 1414/05L colour variation (ΔE): 1,01 residual gloss: 84%	LAB. ID NUMBER: 26255 POWDER COATING: DS 775 HEAT TRANSFER FILM: 2510/05 colour variation (ΔE): 1,85 residual gloss: 61%
Accelerated Weathering Test	Natural Exposure Test	Natural Exposure Test	Natural Exposure Test	Natural Exposure Test	Natural Exposure Test	Natural Exposure Test	Natural Exposure Test
LAB. ID NUMBER: 27763 POWDER COATING: DS-0716S HEAT TRANSFER FILM: 2106/02L Gray scale: 4 residual gloss: 105%	LAB. ID NUMBER: 17736 POWDER COATING: DS 739 HEAT TRANSFER FILM: 2301/02L colour variation (ΔE): 1,37 residual gloss: 87%	LAB. ID NUMBER: 19063 POWDER COATING: DS 704 M HEAT TRANSFER FILM: 2501/15L colour variation (ΔE): 0,36 residual gloss: 93%	LAB. ID NUMBER: 17332 POWDER COATING: DS-0706S HEAT TRANSFER FILM: 1001/09L colour variation (ΔE): 1,92 residual gloss: 96%	LAB. ID NUMBER: 25619 POWDER COATING: DS-0706S HEAT TRANSFER FILM: 1815/02L colour variation (ΔE): 1,57 residual gloss: 96%	LAB. ID NUMBER: 25674 POWDER COATING: DS 797 HEAT TRANSFER FILM: 2305/17 colour variation (ΔE): 0,59 residual gloss: 97%	LAB. ID NUMBER: 25656 POWDER COATING: DS 742 HEAT TRANSFER FILM: 1704/02 colour variation (ΔE): 1,91 residual gloss: 91%	LAB. ID NUMBER: 32027 POWDER COATING: DS-0718S HEAT TRANSFER FILM: 2105/09 colour variation (ΔE): 2,34 residual gloss: 95%