



Suitability for outdoor use of different combinations between polyurethane Decoral System® Powder coatings and heat transfer film Decoral System® must be assessed on [www.decoral-system.com](http://www.decoral-system.com). (link: **TESTED FOR OUTDOOR USE**) or contacting our laboratory.

# Serie Baltie

L' idoneità all'impiego in esterno degli abbinamenti tra prodotti vernicianti poliuretatici Decoral System® e film sublimatici Decoral System® dovrà essere valutata sul sito internet [www.decoral-system.com](http://www.decoral-system.com) (alla voce **FINITURE ADATTE PER USO ESTERNO**) oppure contattando il nostro laboratorio.



*Powder Coating: 9G-233-A005 + Heat Transfer Film: 2512/02*



*Powder Coating: 8G-165-A005 + Heat Transfer Film: 2512/02*



*Powder Coating: DS 768 + Heat Transfer Film: 2512/02*



*Powder Coating: 9G-148-A009 + Heat Transfer Film: 2512/02*



*Powder Coating: MIRROR-155S + Heat Transfer Film: 2512/02*



*Powder Coating: DS 726 + Heat Transfer Film: 2512/02*

# Serie Baltic

Test Report: Accelerated Weathering Test		Decoral LAB Research and Development		68
Laboratory Test	No. 519	Device: Solar 3000e	Total duration: 1009 h	
LAB. ID NUMBER: 43314 POWDER COATING: DS 726 HEAT TRANSFER FILM: 2512/02 Colour Variation (ΔE): 1,19 residual gloss: 95%				
<b>Technical Remarks</b> Excellent residual gloss and low colour variation (ΔE), after 1009 hours.			<b>Technical Opinion:</b> <b>Suitable for OUTDOOR USE</b>	
<small>Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.</small>				
<small>Mod_TR_01_rev03    Laboratory Decoral System    Date: 29/11/2018    ID Report: TR-IA-68-2018</small>				

Test Report: Accelerated Weathering Test		Decoral LAB Research and Development		69
Laboratory Test	No. 519	Device: Solar 3000e	Total duration: 1009 h	
LAB. ID NUMBER: 43316 POWDER COATING: Mirror-155S HEAT TRANSFER FILM: 2512/02 Colour Variation (ΔE): 1,11 residual gloss: 100%				
<b>Technical Remarks</b> Excellent residual gloss and low colour variation (ΔE), after 1009 hours.			<b>Technical Opinion:</b> <b>Suitable for OUTDOOR USE</b>	
<small>Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.</small>				
<small>Mod_TR_01_rev03    Laboratory Decoral System    Date: 29/11/2018    ID Report: TR-IA-69-2018</small>				

Test Report: Accelerated Weathering Test		Decoral LAB Research and Development		70
Laboratory Test	No. 519	Device: Solar 3000e	Total duration: 1009 h	
LAB. ID NUMBER: 43317 POWDER COATING: BG-233-A00S HEAT TRANSFER FILM: 2512/02 Colour Variation (ΔE): 1,68 residual gloss: 100%				
<b>Technical Remarks</b> Excellent residual gloss and low colour variation (ΔE), after 1009 hours.			<b>Technical Opinion:</b> <b>Suitable for OUTDOOR USE</b>	
<small>Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.</small>				
<small>Mod_TR_01_rev03    Laboratory Decoral System    Date: 29/11/2018    ID Report: TR-IA-70-2018</small>				

Test Report: Accelerated Weathering Test		Decoral LAB Research and Development		71
Laboratory Test	No. 519	Device: Solar 3000e	Total duration: 1009 h	
LAB. ID NUMBER: 43318 POWDER COATING: BG-165-A00S HEAT TRANSFER FILM: 2512/02 Colour Variation (ΔE): 0,91 residual gloss: 92%				
<b>Technical Remarks</b> Excellent residual gloss and low colour variation (ΔE), after 1009 hours.			<b>Technical Opinion:</b> <b>Suitable for OUTDOOR USE</b>	
<small>Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.</small>				
<small>Mod_TR_01_rev03    Laboratory Decoral System    Date: 29/11/2018    ID Report: TR-IA-71-2018</small>				

Test Report: Accelerated Weathering Test		Decoral LAB Research and Development		72
Laboratory Test	No. 519	Device: Solar 3000e	Total duration: 1009 h	
LAB. ID NUMBER: 43319 POWDER COATING: DS 788 HEAT TRANSFER FILM: 2512/02 Colour Variation (ΔE): 1,26 residual gloss: 91%				
<b>Technical Remarks</b> Excellent residual gloss and low colour variation (ΔE), after 1009 hours.			<b>Technical Opinion:</b> <b>Suitable for OUTDOOR USE</b>	
<small>Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.</small>				
<small>Mod_TR_01_rev03    Laboratory Decoral System    Date: 29/11/2018    ID Report: TR-IA-72-2018</small>				

Test Report: Accelerated Weathering Test		Decoral LAB Research and Development		73
Laboratory Test	No. 519	Device: Solar 3000e	Total duration: 1009 h	
LAB. ID NUMBER: 43320 POWDER COATING: BG-14S-A00S HEAT TRANSFER FILM: 2512/02 Colour Variation (ΔE): 1,2 residual gloss: 90%				
<b>Technical Remarks</b> Excellent residual gloss and low colour variation (ΔE), after 1009 hours.			<b>Technical Opinion:</b> <b>Suitable for OUTDOOR USE</b>	
<small>Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.</small>				
<small>Mod_TR_01_rev03    Laboratory Decoral System    Date: 29/11/2018    ID Report: TR-IA-73-2018</small>				