

Suitability for outdoor use of different combinations between **polyurethane Decoral System[®] Powder coatings** and **heat transfer film Decoral System[®]** must be assessed on www.decoral-system.com. (link: **TESTED FOR OUTDOOR USE**) or contacting our laboratory.



Powder Coating: 8G-168-A005 + Heat Transfer Film: 2117/23



Powder Coating: 8G-168-A005 + Heat Transfer Film: 2507/07



Powder Coating: 8G-168-A005 + Heat Transfer Film: 2120/03



Powder Coating: 8G-168-A005 + Heat Transfer Film: 2512/02



Powder Coating: 8G-168-A005 + Heat Transfer Film: 2533/09





Powder Coating: 8G-168-A005 + Heat Transfer Film: 2501/05

L' idoneità all'impiego in esterno degli abbinamenti tra **prodotti vernicianti poliuretani Decoral System[®]** e **film sublimatici Decoral System[®]** dovrà essere valutata sul sito internet www.decoral-system.com (alla voce **FINITURE ADATTE PER USO ESTERNO**) oppure contattando il nostro laboratorio.


ATACAMA


Test Report: Accelerated Weathering Test		Decoral LAB Research and Development		80	
Laboratory Test	No. 598	Device: Q8sun 3000	Total duration: 1166h		
					
LAB. ID NUMBER: 51457 POWDER COATING: SG-168-A005 HEAT TRANSFER FILM: 250707 Colour Variation (ΔE): 2.38 residual gloss: 79%					
Technical Remarks Good residual gloss and low colour variation (ΔE), after 1166 hours.				Technical Opinion: Suitable for OUTDOOR USE	
Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.					
Mod_TR_01_rev03 Laboratory Decoral System Date: 14/12/2021 ID Report: TR-IA-80-2021					

Test Report: Accelerated Weathering Test		Decoral LAB Research and Development		78	
Laboratory Test	No. 598	Device: Q8sun 3000	Total duration: 1166h		
					
LAB. ID NUMBER: 51457 POWDER COATING: SG-168-A005 HEAT TRANSFER FILM: 250105 Colour Variation (ΔE): 1.48 residual gloss: 79%					
Technical Remarks Good residual gloss and low colour variation (ΔE), after 1166 hours.				Technical Opinion: Suitable for OUTDOOR USE	
Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.					
Mod_TR_01_rev03 Laboratory Decoral System Date: 14/12/2021 ID Report: TR-IA-78-2021					

Test Report: Accelerated Weathering Test		Decoral LAB Research and Development		73	
Laboratory Test	No. 598	Device: Q8sun 3000	Total duration: 1166h		
					
LAB. ID NUMBER: 51444 POWDER COATING: SG-168-A005 HEAT TRANSFER FILM: 253309 Colour Variation (ΔE): 1.84 residual gloss: 77%					
Technical Remarks Good residual gloss and low colour variation (ΔE), after 1166 hours.				Technical Opinion: Suitable for OUTDOOR USE	
Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.					
Mod_TR_01_rev03 Laboratory Decoral System Date: 14/12/2021 ID Report: TR-IA-73-2021					

Test Report: Accelerated Weathering Test		Decoral LAB Research and Development		74	
Laboratory Test	No. 598	Device: Q8sun 3000	Total duration: 1166h		
					
LAB. ID NUMBER: 51445 POWDER COATING: SG-168-A005 HEAT TRANSFER FILM: 212003 Colour Variation (ΔE): 1.38 residual gloss: 81%					
Technical Remarks Good residual gloss and low colour variation (ΔE), after 1166 hours.				Technical Opinion: Suitable for OUTDOOR USE	
Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.					
Mod_TR_01_rev03 Laboratory Decoral System Date: 14/12/2021 ID Report: TR-IA-74-2021					

Test Report: Accelerated Weathering Test		Decoral LAB Research and Development		76	
Laboratory Test	No. 598	Device: Q8sun 3000	Total duration: 1166h		
					
LAB. ID NUMBER: 51454 POWDER COATING: SG-168-A005 HEAT TRANSFER FILM: 211723 Colour Variation (ΔE): 1.17 residual gloss: 79%					
Technical Remarks Good residual gloss and low colour variation (ΔE), after 1166 hours.				Technical Opinion: Suitable for OUTDOOR USE	
Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.					
Mod_TR_01_rev03 Laboratory Decoral System Date: 14/12/2021 ID Report: TR-IA-76-2021					

Test Report: Accelerated Weathering Test		Decoral LAB Research and Development		77	
Laboratory Test	No. 598	Device: Q8sun 3000	Total duration: 1166h		
					
LAB. ID NUMBER: 51456 POWDER COATING: SG-168-A005 HEAT TRANSFER FILM: 251202 Colour Variation (ΔE): 1.82 residual gloss: 72%					
Technical Remarks Good residual gloss and low colour variation (ΔE), after 1166 hours.				Technical Opinion: Suitable for OUTDOOR USE	
Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.					
Mod_TR_01_rev03 Laboratory Decoral System Date: 14/12/2021 ID Report: TR-IA-77-2021					