


 **Laboratory  
Test**

**No. 600**

 **Device:  
QSun 3000**

 **Total duration:  
1303h**



LAB. ID NUMBER: 50637  
POWDER COATING: 9G-301-A004  
HEAT TRANSFER FILM: 6054/01  
Colour Variation ( $\Delta E$ ): **0,43**  
residual gloss: **100%**

**Technical Remarks**

Excellent residual gloss and low colour variation ( $\Delta E$ ),  
after 1303 hours.

Technical Opinion:

**Suitable for  
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.