



Laboratory
Test


No. 551



Device:
Solar 3000eN



Total duration:
1156 h



LAB. ID NUMBER: 45204
POWDER COATING: DS-0768S
HEAT TRANSFER FILM: 1407/01
Colour variation (ΔE): **3,60**
residual gloss: **71%**

Technical Remarks

Good residual gloss but high colour variation isn't acceptable for outdoor use.

Technical Opinion:

**NOT for
outdoor use**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.