



Laboratory  
Test

No. 351



Device:  
Solar 3000e



Total duration:  
1164h

Unexposed area  
(reference)

Exposed  
area



LAB. ID NUMBER: 27379  
POWDER COATING: DS 450  
HEAT TRANSFER FILM: --  
colour variation ( $\Delta E$ ): **0,39**  
residual gloss: **93%**

Unexposed area  
(reference)

Exposed  
area



LAB. ID NUMBER: 27380  
POWDER COATING: DS 450  
HEAT TRANSFER FILM: 1806/01  
colour variation ( $\Delta E$ ): **0,85**  
residual gloss: **85%**

### Technical Remarks

Excellent residual gloss and very low colour variation ( $\Delta E$ ), after 1164 hours.

Technical Opinion:

**Suitable for  
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.