



Laboratory  
Test


No. 454



Device:  
Sol 3000eN



Total duration:  
1268h



LAB. ID NUMBER: 38205  
POWDER COATING: DS 772  
HEAT TRANSFER FILM: 1807/01  
Colour Variation ( $\Delta E$ ): **1,58**  
residual gloss: **76%**

### Technical Remarks

Good residual gloss and low colour variation ( $\Delta E$ ),  
after 1268 hours.

Technical Opinion:

**Suitable for  
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.