



Laboratory
Test

No. 527



Device:
Solar 3000e



Total duration:
1148 h



LAB. ID NUMBER: 43474
POWDER COATING: DS 1753
HEAT TRANSFER FILM: 1818/24
Colour Variation (ΔE): **1,89**
residual gloss: **80%**

Technical Remarks

Good residual gloss and low colour variation (ΔE),
after 1148 hours.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.