



Laboratory
Test

No. 556



Device:
QSun 3000



Total duration:
1071 h



LAB. ID NUMBER: 45729
POWDER COATING: DS 721
HEAT TRANSFER FILM: 1421/08
Colour Variation (ΔE): **1,92**
residual gloss: **95%**

Technical Remarks

Excellent residual gloss and low colour variation (ΔE), after 1071 hours.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.