



Laboratory
Test

No. 321



Device:
QSun 3000



Total duration:
1152h

Unexposed area
(reference)

Exposed
area



Unexposed area
(reference)

Exposed
area



LAB. ID NUMBER: 26299
POWDER COATING: DS 439L
HEAT TRANSFER FILM: --
colour variation (ΔE): **0,45**
residual gloss: **95%**

LAB. ID NUMBER: 26300
POWDER COATING: DS 439L
HEAT TRANSFER FILM: 1603/02L
colour variation (ΔE): **1,22**
residual gloss: **97%**

Technical Remarks

Excellent residual gloss and very low colour variation (ΔE), after 1152 hours.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.