



Laboratory
Test


No. 288



Device:
Qsun 3000



Total duration:
950h



LAB. ID NUMBER: 24187
POWDER COATING: DS 772
HEAT TRANSFER FILM: 2401/04L
colour variation (ΔE): **0,76**
residual gloss: **91%**

Technical Remarks

Excellent residual gloss and very low colour variation (ΔE),
after 950 hours, on both coatings.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.