



Laboratory
Test

No. 417



Device:
Sola 1500e



Total duration:
866h



LAB. ID NUMBER: 34962
POWDER COATING: DS 1742
HEAT TRANSFER FILM: 2601/01
colour variation (ΔE): **1,72**
residual gloss: **70%**

Technical Remarks

Excellent residual gloss and low colour variation (ΔE),
after 866 hours.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.