



Laboratory
Test

No. 369




Device:
QSun 3000



Total duration:
886h


Unexposed area
(reference)

Exposed
area



Unexposed area
(reference)

Exposed
area



LAB. ID NUMBER: 29613
POWDER COATING: Subliwallsky-739
HEAT TRANSFER FILM: --
Grey scale: 5
residual gloss: 93%

LAB. ID NUMBER: 29616
POWDER COATING: Subliwallsky-739
HEAT TRANSFER FILM: 2503/09
Grey scale: 4
residual gloss: 97%

Technical Remarks

Excellent residual gloss and very low colour variation, after 886 hours.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.