



Laboratory
Test

No. 369



Device:
QSun 3000



Total duration:
886h

Unexposed area
(reference)

Exposed
area



LAB. ID NUMBER: 29607
POWDER COATING: Subliwallsky-733
HEAT TRANSFER FILM: --
Grey scale: 5
residual gloss: 93%

Unexposed area
(reference)

Exposed
area



LAB. ID NUMBER: 29610
POWDER COATING: Subliwallsky-733
HEAT TRANSFER FILM: 2103/01
Grey scale: 4/5
residual gloss: 91%

Technical Remarks

Excellent residual gloss and very low colour variation, after 886 hours.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.