



Laboratory  
Test


No. 293



Device:  
QSun 3000



Total duration:  
919h



LAB. ID NUMBER: 24235  
POWDER COATING: DS-0831S  
HEAT TRANSFER FILM: 6001/01L  
colour variation ( $\Delta E$ ): **4,53**  
residual gloss: **100%**

### Technical Remarks

Excellent residual gloss but not acceptable colour variation ( $\Delta E$ ),  
after 919 hours, for coating samples

Technical Opinion:

**NOT for  
outdoor use**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.