



Laboratory  
Test


No. 372



Device:  
QSun 3000



Total duration:  
1209h



LAB. ID NUMBER: 30163  
POWDER COATING: DS 716  
HEAT TRANSFER FILM: 2505/02  
Colour variation( $\Delta E$ ): 1,4  
residual gloss: 64%

### Technical Remarks

Good residual gloss and very low colour variation ( $\Delta E$ ), after 1209 hours on decorated sample.

Technical Opinion:

**Suitable for  
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.