



Laboratory  
Test

No. 393



Device:  
Sola 1500e



Total duration:  
1160h



LAB. ID NUMBER: 32750  
POWDER COATING: 8G-055-A005  
HEAT TRANSFER FILM: 2301/07  
colour variation ( $\Delta E$ ): **0,65**  
residual gloss: **91%**

### Technical Remarks

Excellent residual gloss and low colour variation ( $\Delta E$ ),  
after 1160 hours.

Technical Opinion:

**Suitable for  
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.