



Laboratory  
Test


No. 330



Device:  
QSun 3000



Total duration:  
1111h



LAB. ID NUMBER: 26555  
POWDER COATING: DS-0405S  
HEAT TRANSFER FILM: 2805/02  
colour variation ( $\Delta E$ ): **3,93**  
residual gloss: **100%**

### Technical Remarks

Residual gloss is excellent but colour variation ( $\Delta E$ ) is not acceptable for outdoor use.

Technical Opinion:

**NOT for  
outdoor use**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.