



Laboratory
Test


No. 609



Device:
QSun 3000



Total duration:
1241h



LAB. ID NUMBER: 51547
POWDER COATING: DS 706
HEAT TRANSFER FILM: 2805/03
Colour Variation (ΔE): **0,81**
residual gloss: **78%**

Technical Remarks

Good residual gloss and normal colour variation (ΔE),
after 1241 hours.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.