



Laboratory
Test



No. 327



Device:
QSun 3000



Total duration:
1263h



LAB. ID NUMBER: 26397
POWDER COATING: DS-0718S
HEAT TRANSFER FILM: --
Cololor variation (ΔE): **0,26**
residual gloss: **100%**

LAB. ID NUMBER: 26398
POWDER COATING: DS-0718S
HEAT TRANSFER FILM: 2105/09L
Cololor variation (ΔE): **2,78**
residual gloss: **98%**

Technical Remarks

Excellent residual gloss and very low colour variation (ΔE), after 1263 hours.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.