



Laboratory
Test


No. 327



Device:
QSun 3000



Total duration:
1263h



LAB. ID NUMBER: 26396
POWDER COATING: DS 718
HEAT TRANSFER FILM: 2105/09
colour variation (ΔE): **3,41**
residual gloss:50%

Technical Remarks

Residual gloss and colour variation (ΔE) are not acceptable for outdoor use.

Technical Opinion:

**NOT for
outdoor use**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.