



Laboratory  
Test


No. 102



Device:  
QSun 3000



Total duration:  
1242



LAB. ID NUMBER: 18547  
POWDER COATING: PE 411 + DS-0810S  
HEAT TRANSFER FILM: 5001/01L  
colour variation ( $\Delta E$ ): **2,23**  
residual gloss: **99%**

### Technical Remarks

Excellent residual gloss and very low colour variation ( $\Delta E$ ), after 1242 hours on decorated sample.

Technical Opinion:

**Suitable for  
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.