



Laboratory  
Test

No. 384



Device:  
Sol 1500En



Total duration:  
1351H



LAB. ID NUMBER: 31828  
POWDER COATING: DS 472  
HEAT TRANSFER FILM: 1414/05  
Colour Variation ( $\Delta E$ ): **2,31**  
residual gloss: **89%**

#### Technical Remarks

Good residual gloss and low colour variation ( $\Delta E$ ),  
after 1351 hours.

Technical Opinion:

**Suitable for  
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.