



Laboratory  
Test


No. 374



Device:  
Solar 1500eN



Total duration:  
1348h



LAB. ID NUMBER: 29740  
POWDER COATING: DS-0402S  
HEAT TRANSFER FILM: 2533/02  
Colour variation( $\Delta E$ ): **1,36**  
residual gloss: **79%**

### Technical Remarks

Excellent residual gloss and very low colour variation ( $\Delta E$ ), after 1348 hours on decorated sample.

Technical Opinion:

**Suitable for  
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.